

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
26 August 2004 (26.08.2004)

PCT

(10) International Publication Number
WO 2004/072376 A1

(51) International Patent Classification⁷: **D21H 17/72**,
23/76 // 17:29, 17:42, 17:55, 21:20, 21:24

(21) International Application Number:
PCT/US2004/003412

(22) International Filing Date: 6 February 2004 (06.02.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/445,970 7 February 2003 (07.02.2003) US

(71) Applicant (for all designated States except US): **BAYER
CHEMICALS CORPORATION** [US/US]; 100 Bayer
Road, Pittsburgh, PA 15205-9741 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **RYAN, Michael**
[US/US]; 3 West Farm Ridge, Newtown, CT 06470 (US).
BREVARD, William [US/US]; 90 Courtland Hill Street,
Stamford, CT 06906 (US).

(74) Agents: **AKORLI, Godfried, R.** et al.; Bayer Chemicals
Corporation, 100 Bayer Road, Pittsburgh, PA 15205-9741
(US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **ANIONIC FUNCTIONAL PROMOTER AND CHARGE CONTROL AGENT WITH IMPROVED WET TO DRY TEN-
SILE STRENGTH RATIO**

(57) Abstract: The invention relates to a composition comprising (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000; (b) a cationic surfactant component; such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant. The invention also relates to a paper product made with such a system, and method for imparting wet strength to a paper product with the functional promoter.

WO 2004/072376 A1

JC14 Rec'd PCT/PTO 20 JUL 2005

ANIONIC FUNCTIONAL PROMOTER
AND CHARGE CONTROL AGENT WITH IMPROVED WET TO DRY
TENSILE STRENGTH RATIO

BACKGROUND

The paper industry currently has no synthetic solution adjunctive to cationic wet strength resins which controls, and preferably improves the wet to dry strength ratio of paper. This ratio is important, as it is a measure of the softness of paper- critical in such products as tissue and towel. Anionic polymers have been shown to improve wet strength of fibrous substrates with the polyamide resin or other cationic strength agents, however, these anionic polymers also improve dry strength thereby maintaining the wet to dry ratio, not improving it. As such, it would be advantageous to develop a composition that enables a market participant to control the wet to dry strength ratio of paper.

SUMMARY

The invention relates to a composition comprising (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000; (b) a cationic surfactant component, such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

In one embodiment, the invention relates to a composition comprising (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight ranging from about 50,000 daltons to about 500,000 daltons and a molecular weight charge index value of more than 10,000 and less than 500,000, (b) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined

weight of the water-soluble anionic polymer and the cationic surfactant component, such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging
5 from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

In another embodiment, the invention relates to a composition
10 comprising a wet-strength enhancing amount of (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000, (b) a cationic surfactant component present in an
15 amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component; and (c) a cationic strength component, such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry
20 tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

In another embodiment, the invention relates to a paper product comprising the reaction product of: (a) a cationic strength component,
25 (b) a fibrous substrate component, and (c) a composition comprising (1) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000 and (2) a cationic surfactant component; such that when the composition treats a fibrous substrate, in
30 conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to

when the fibrous substrate is treated with the functional promoter and without a surfactant.

In another embodiment, the invention relates to a method for making a paper product comprising adding to a pulp slurry containing a fibrous substrate component a composition comprising: a) a composition comprising (1) a functional promoter comprising (i) a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000, (2) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component, and (3) a cationic strength component, such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

These and other features, aspects, and advantages of the present invention will become better understood with reference to the following description and appended claims.

DESCRIPTION

The invention is based on the discovery that the use of a functional promoter, in conjunction with a cationic surfactant component, enables the user to achieve full to nearly full wet strength promotion while significantly moderating dry strength promotion.

This significant practical benefit was quite unexpected for a number of reasons. A cationic material will often precipitate an anionic polymer, however, in these studies, the combination formed a homogeneous solution. Additionally, cationic surfactants will often decrease the wet strength of fibrous substrates containing cationic wet strength agents, however, the combination of cationic surfactant with the anionic polymer allows full to nearly full promotion of the cationic strength agent yielding

moderated dry tensile yet high wet tensile. Advantageously, the inclusion of optimal amounts of cationic surfactants in the composition allows the use to achieve full to nearly full wet strength promotion while significantly moderating dry strength promotion. The inclusion of the cationic surfactants in the anionic polymer composition allows the product greater application flexibility.

The functional promoter is generally a water-soluble anionic polymer or a water-dispersible polymer having a molecular weight that is at least about 50,000 daltons and a molecular weight charge index value that is at least about 10,000. This material is described in U.S.S.N. 10/174,964, incorporated herein by reference in its entirety. As used herein, the term "charge" refers to the molar weight percent of anionic monomers in a functional promoter. For instance, if a functional promoter is made with 30 mole % anionic monomer, the charge of the functional promoter is 30%.

The phrase "molecular weight charge index value" means the value of the multiplication product of the molecular weight and the charge of a functional promoter. For instance, a functional promoter having a molecular weight of 100,000 daltons and a charge of 20% has a molecular weight charge index value that is 20,000. All molecular weights discussed herein are weight average molecular weights. The average molecular weight of a functional promoter can be measured by size exclusion chromatography. When the functional promoter is used in conjunction with a cationic strength agent, the resulting composition imparts improved wet strength to paper products as compared to when the cationic strength agent is used in conjunction with a water-soluble anionic polymer that does not have a molecular weight that is at least about 50,000 daltons and a molecular weight charge index value that is at least about 10,000.

Examples of suitable anionic polymers having a molecular weight that is at least about 50,000 daltons and a molecular weight charge index value that is at least about 10,000 include specific anionic water-soluble or water-dispersible polymers and copolymers of acrylic acid and methacrylic acid, e.g., acrylamide-acrylic acid, methacrylamide-acrylic acid,

acrylonitrile-acrylic acid, methacrylonitrile-acrylic acid, provided, of course, that the polymers meet the required molecular weight and molecular weight charge index value. Other examples include copolymers involving one of several alkyl acrylates and acrylic acid, copolymers involving one of several alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate or hydroxyalkyl methacrylate copolymers, copolymers involving one of several alkyl vinyl ethers and acrylic acid, and similar copolymers in which methacrylic acid is substituted in place of acrylic acid in the above examples, provided, of course, that the polymers meet the required molecular weight and molecular weight charge index value. Other examples of suitable anionic polymers having a molecular weight that is at least about 50,000 daltons and a molecular weight charge index value that is at least about 10,000 include those anionic polymers made by hydrolyzing an acrylamide polymer or by polymerizing monomers such as (methyl) acrylic acid and their salts, 2-acrylamido-2-methylpropane sulfonate, sulfoethyl-(meth)acrylate, vinylsulfonic acid, styrene sulfonic acid, maleic or other dibasic acids or their salts or mixtures thereof. Additionally, crosslinking agents such as methylene bisacrylamide may be used, provided, of course, that the polymers meet the above-mentioned molecular weight and molecular weight charge index value.

The functional promoter is made by polymerizing anionic monomers, and non-ionic monomers in the presence of an initiator component and a suitable solvent component under conditions that produce an anionic polymer having a molecular weight that is at least about 50,000 daltons and a molecular weight charge index value that is at least about 10,000. During the preparation of the functional promoter, it is critical that the charge and the molecular weight be controlled so that the resulting polymer has a proper molecular weight and a proper molecular weight charge index value. The charge of the anionic polymer is generally controlled by adjusting the ratios of the anionic monomers and the non-ionic monomers. The molecular weight of the anionic polymer, on the other hand, is adjusted by adjusting the polymerization initiator or a chain-transfer agent.

The way the initiator system is adjusted will depend on the initiator system that is used. If a redox-based initiator is used, for instance, the initiator system is adjusted by adjusting the ratio and the amount of initiator and a co-initiator. If an azo-based initiator system is used, adjustment of the azo-compound will determine the molecular weight of the anionic polymer. Alternatively, a chain transfer agent can be used in conjunction with a redox-based initiator or an azo-based initiator to control the molecular weight of the anionic polymer. Provided that the monomers and initiator components are adjusted to make an anionic polymer having the required molecular weight and molecular weight charge index value, known methods for making acrylic-acrylamide polymers can be modified accordingly to make the functional promoter.

The molecular weight of the functional promoter can differ. In one embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 5,000,000 daltons, or from about 50,000 to about 4,000,000 daltons, or from about 50,000 to about 3,000,000 daltons, or from about 50,000 to about 2,000,000 daltons, or from about 50,000 to about 1,500,000 daltons, or from about 50,000 to about 1,000,000 daltons. In one embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 750,000 daltons. In another embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 650,000 daltons. In another embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 500,000 daltons. In another embodiment, the functional promoter has a molecular weight ranging from about 300,000 to about 500,000 daltons. In another embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 250,000 daltons. In another embodiment, the functional promoter has a molecular weight ranging from about 50,000 to about 100,000 daltons. When the functional polymer is in solution, the molecular weight of the functional promoter is preferably less than 5,000,000 daltons.

Similarly, the molecular weight charge index value of the functional promoter can differ. In one embodiment, the functional promoter has a

molecular weight charge index value ranging from about 10,000 to about 1,000,000. In another embodiment, the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 500,000. In another embodiment, the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 450,000. In another embodiment, the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 300,000. In another embodiment, the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 150,000. In another embodiment, the functional promoter has a molecular weight charge index value ranging from about 25,000 to about 100,000. In one embodiment, the charge of the functional promoter is at least 50%.

When used in an aqueous solution, the functional promoter generally has a viscosity that is less than 2,500 cP and more than 25 cP when the solution has a concentration of 15% by weight of the functional promoter. The polymer solution was diluted to 15% using deionized water. The viscosity was then measured using a Brookfield DVII instrument with spindle #2 at 12 rpm at 25 °C.


The cationic surfactant component can be any cationic material, which when used in accordance with the invention, provides a composition of the invention. Examples of suitable cationic materials include alkylated quaternary amines, alkyl aryl quaternary amines, alkoxyated quaternary amines, imidazolinium quaternary amines, functionalized polysiloxanes, and combinations thereof.

The cationic surfactant component is used in an amount that is at least about 5 % , based on the total weight of the composition. In one embodiment, the cationic surfactant component is ranging from about 10 % to about 50%, based on the total weight of the composition. In another embodiment, the cationic surfactant component is present in an amount ranging from about 5% to about 40%, or from about 20% to about 40%, based on the total weight of the composition.

The cationic strength component includes a cationic resin, which when used in conjunction with the functional promoter, has an improved

wet strength-imparting capacity, as compared to when the cationic strength agent is used in conjunction with a water-soluble anionic polymer that does not have a molecular weight that is at least about 50,000 daltons and does not have a molecular weight charge index value that is more
 5 than 10,000.

The cationic strength component can include any polyamide wet strength resin, which when used in conjunction with a functional promoter, exhibits increased wet-strength imparting properties. Useful cationic thermosetting polyamide-epichlorohydrin resins include a water-soluble
 10 polymeric reaction product of epichlorohydrin and a polyamide derived from a polyalkylene polyamine and a C₃-C₁₀ saturated aliphatic dicarboxylic acid, an aromatic dicarboxylic acid, oxalic acid, or urea. In the preparation of these cationic thermosetting resins, the dicarboxylic acid first reacts with the polyalkylene polyamine under conditions that produce
 15 a water-soluble polyamide containing the recurring groups:



in which n and x are each 2 or more and R is the divalent hydrocarbon radical of the dicarboxylic acid. This water-soluble polyamide then reacts with epichlorohydrin to form the water-soluble cationic thermosetting resin.

20 Other patents teaching the preparation and/or use of aminopolyamide-epichlorohydrin resins in wet strength paper applications include U.S. Pat. Nos. 5,239,047, 2,926,154, 3,049,469, 3,058,873, 3,066,066, 3,125,552, 3,186,900, 3,197,427, 3,224,986, 3,224,990, 3,227,615, 3,240,664, 3,813,362, 3,778,339, 3,733,290, 3,227,671, 3,239,491,
 25 3,240,761, 3,248,280, 3,250,664, 3,311,594, 3,329,657, 3,332,834, 3,332,901, 3,352,833, 3,248,280, 3,442,754, 3,459,697, 3,483,077, 3,609,126, and 4,714,736; British patents 1,073,444 and 1,218,394; Finnish patent 36,237 (CA 65: 50543d); French patent 1,522,583 (CA 71: 82835d); German patents 1,906,561 (CA 72: 45235h), 2,938,588 (CA 95: 9046t), 3,323,732 (CA 102: 151160c); Japanese patents 70 27,833 (CA
 30 74: 4182m), 71 08,875 (CA 75: 49990k), 71 12,083 (CA 76: 115106a); 71 12,088 (CA 76: 115107b), 71 36,485 (CA 77: 90336f); Netherlands

application 6,410,230 (CA 63: P5858h); South African patent 68 05,823 (CA 71: 114420h); and Swedish patent 210,023 (CA 70: 20755y).

Other suitable cationic strength agents include cationic polyvinyl-amides suitable for reaction with glyoxal, including those which are
5 produced by copolymerizing a water-soluble vinylamide with a vinyl, water-soluble cationic monomer when dissolved in water, e.g., 2-vinylpyridine, 2-vinyl-N-methylpyridinium chloride, diallyldimethylammonium chloride, (p-vinylphenyl)-trimethylammonium chloride, 2-(dimethylamino)ethyl acrylate, methacrylamide propyl trimethyl ammonium chloride, and the like.

10 Alternatively, glyoxylated cationic polymers may be produced from non-ionic polyvinylamides by converting part of the amide substituents thereof (which are non-ionic) to cationic substituents. One such polymer can be produced by treating polyacrylamide with an alkali metal hypohalite, in which part of the amide substituents are degraded by the
15 Hofmann reaction to cationic amine substituents (see U.S. Pat. No. 2,729,560). Another example is the 90:10 molar ratio acrylamide; p-chloromethylstyrene copolymer which is converted to a cationic state by quaternization of the chloromethyl substituents with trimethylamine. The trimethylamine can be replaced in part or in whole with triethanolamine or
20 other water-soluble tertiary amines. Alternatively still, glyoxylated cationic polymers can be prepared by polymerizing a water-soluble vinyl tertiary amine (e.g., dimethylaminoethyl acrylate or vinylpyridine) with a water-soluble vinyl monomer copolymerizable therewith, e.g., acrylamide, thereby forming a water-soluble cationic polymer. The tertiary amine
25 groups can then be converted into quaternary ammonium groups by reaction with methyl chloride, dimethyl sulfate, benzyl chloride, and the like, in a known manner, and thereby producing an enhancement of the cationic properties of the polymer. Moreover, polyacrylamide can be rendered cationic by reaction with a small amount of glycidyl dimethyl-
30 ammonium chloride.

The composition is made by any method that enables the functional promoter and the cationic surfactant component to be combined so that the composition forms. Preferably, the composition is made by

simply blending the surfactant into the anionic polymer solution homogeneously.

The composition and the cationic strength component are used in amounts sufficient to enhance the wet strength of a paper product. The specific amount of the composition and the cationic strength component will depend on, among other things, the type of pulp properties. The ratio of the functional promoter to the cationic strength component may range from about 1/20 to about 1/1, preferably from about 2/1 to about 1/10, and more preferably about 1/4. The ratio of the cationic surfactant component to the functional promoter may range from about 1/20 to about 1/2, preferably from about 1/10 to about 1/2, and more preferably about 1/3.

The fibrous substrate of the invention can include any fibrous substrate of a pulp slurry used to make paper products. Generally, the invention can be used in slurries for making dry board, fine paper, towel, tissue, and newsprint products. Dry board applications include liner board, medium board, bleach board, and corrugated board products.

The paper products produced according to the invention may contain known auxiliary materials that can be incorporated into a paper product such as a paper sheet or a board by addition to the pulp at the wet end, directly to the paper or board or to a liquid medium, e.g., a starch solution, which is then used to impregnate a paper sheet or a board. Representative examples of auxiliary agents include defoamers, bacteriocides, pigments, fillers, and the like.

In use, the invention provides a method for imparting wet strength to a paper product a wet-strength enhancing amount of (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000, (b) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component; and (c) a cationic strength component, such that when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a

ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant

5 The cationic strength component and the composition each are generally added to a dilute aqueous suspension of paper pulp and the pulp is subsequently sheeted and dried in a known manner. Preferably, the cationic strength component and the composition are added in dilute aqueous solutions. More particularly, the cationic strength component and
10 the composition are desirably added to the slurry in the form of dilute aqueous solutions at solids concentrations that are at least about 0.2%, preferably from about 1.5 to about 0.5 %. The papermaking system (pulp slurry and dilution water) may be acidic, neutral or alkaline. The preferred pH range is from about 4.5 to 8. The cationic strength agent can be used
15 with cationic performance agents such as cationic starch. The dosages at which the composition and the cationic strength component are added varies, depending on the application. Generally, the dosage of the composition is at least about 0.1 lb/ton (0.005 wt%). The functional promoter dosage can range from about 0.1 lb/ton (0.005 wt%) to about 20
20 lbs/ton (1 wt%), or from about 3 lbs/ton (0.15 wt%) to about 20 lbs/ton (0.75 wt%), or from about 4 lbs/ton (0.2 wt%) to about 20 lbs/ton (1 wt%), or from about 2 lbs/ton (0.1 wt%) to about 5 lbs/ton (0.25 wt%). The dosage at which the cationic strength component is added is generally at least 0.1 lb/ton (0.005 wt%). The cationic strength component dosage can
25 range from about 0.1 lb/ton (0.005 wt%) to about 100 lbs/ton (5 wt%), or from about 5 lbs/ton (0.25 wt%) to about 50 lbs/ton (2.5 wt%), or from about 10 lbs/ton (0.5 wt%) to about 30 lbs/ton (1.5 wt%), or from about 10 lbs/ton (0.5 wt%) to about 24 lbs/ton (1.2 wt%).

30 The composition may be added into a pulp slurry by any suitable means. Preferably, the composition is added after the cationic strength agent component is added. However, the composition may be added either before or after the cationic strength agent, still yielding excellent performance. This significant practical benefit was quite unexpected.

The invention provides valuable benefits to the industry. This invention, depending on the application, can provide desired wet tensile strength:dry tensile strength ratios to a paper product. The invention can also allow for the use of lower polyamide resin dosages, thereby decreasing undesirable volatile organic compound (VOC) and dichloropropanol (DCP) levels. The effectiveness of the composition substantially reduces or eliminates the need to use carboxymethylcellulose, and thereby avoids the disadvantages of using carboxymethylcellulose. The functional promoter is synthetic and, therefore, the charge and molecular weight are controllable. Also, it is a "pump-and-go" solution, and thereby is a flexible practical solution. The invention can also be effective at a lower dose than carboxymethyl-cellulose and is a more effective charge control agent. Although the invention is useful in imparting wet strength to paper products, the invention can also impart dry strength to paper products.

The invention is further described in the following illustrative examples in which all parts and percentages are by weight unless otherwise indicated.

EXAMPLES

EXAMPLE 1

Preparation of a Poly (acrylamide₅₀-co-acrylic acid₅₀)

28.93 parts acrylic acid, 53.15 parts acrylamide (53.7% solution in water), 0.06 parts ethylenediaminetetraacetic acid disodium salt, and 17.9 parts water were charged to vessel "A" and agitated. The pH of the resulting mixture was adjusted to pH 4.0 using caustic soda. 0.28 parts ammonium persulfate in water solution were charged to vessel "B" and 0.84 parts sodium metabisulfite in water solution were charged to vessel "C." 119.76 parts water were charged to a reactor heel and agitated. The heel was brought to reflux and vessels A, B and C were charged to the reactor continuously over a 72-minute period. The reflux was continued for 30 minutes after the charges were completed. The molecular weight of

the polymer was approximately 111,000 daltons. The charge of the polymer was approximately 50%.

5 EXAMPLE 2

Preparation of a Glyoxalated Poly (acrylamide-co-acrylic acid)

100.00 parts polymer solution from Example 1 were charged to a reaction vessel and agitated. 18.85 parts glyoxal (40% solution, in water) and 64.60 parts water were charged to a reaction vessel and the pH was adjusted to 8.5 using caustic soda. When the viscosity of the solution reached 26 – 28 seconds in a #3 Shell cup, the reaction was quenched with sulfuric acid to pH 2.9 – 3.1. The charge of the polymer was approximately 50%.

15 EXAMPLE 3

Preparation of Glyoxalated Acrylamide-itaconic acid-Diallyldimethyl Ammonium Chloride Terpolymers

100 parts acrylamide (52.7%), 10.6 parts itaconic acid (99%), 3.13 parts diallyldimethylammonium chloride (58.5%) were charged to a first vessel. Water was then charged to the first reaction vessel and the solution was diluted to 26% solids, and the solution was then agitated and sparged with nitrogen. 5.69 parts 2-mercaptoethanol (98%) were charged to the first reaction vessel and agitated. 9.32 parts ammonium persulfate (13.3%) were charged into the first vessel and maintained at a temperature of 70 °C. 29.1 parts each of ammonium persulfate and sodium metabisulfite (2%) solutions were charged to the first vessel over one hour. The mixture was heated for one hour after completion. 150 parts of this polymer backbone was then charged to a second reaction vessel and agitated. 58.1 parts water and 32.7 parts glyoxal (40%) were charged to the second reaction vessel. The pH was adjusted to 8.3 using caustic soda. At a Shell cup viscosity of 26 – 27 seconds, the pH was reduced to 2.9–3.1 using sulfuric acid.

EXAMPLES 4-16:Wet Strength Evaluation

To evaluate the wet strength of a cationic strength component without use of a functional promoter in accordance to the invention, the following procedure was practiced. 1667 g of 0.6% consistency 50/50 hardwood/ softwood furnish containing 200 ppm sulfates and 50 ppm calcium was adjusted to pH 7.5 using sodium hydroxide. A dilute solution of polyamide resin was mixed into the pulp slurry at the dosage level of 10 lbs/ ton (0.5 wt%) for 30 seconds. To evaluate the wet tensile strength of the paper product formed, three 2.8 g handsheets, each approximately a square having an edge of 8 inches, 64 square inches (416 cm²), were formed from each batch using a Noble & Wood handsheet former. The formed sheets were pressed between felts in the nip of press rolls, and then drum dried on a rotary drier for one minute at 240°F (116°C). The sheets were conditioned at 73 °F (23 °C) and 50% relative humidity before measuring the wet tensile using a Thwing-Albert tensile tester. The wet tensile strength of the paper was determined.

To evaluate how a functional promoter with different molecular weight and charge properties would impact the wet strength of the paper product, the procedure described above was repeated, except that dilute solutions containing anionic polymers indicated below in Tables 1 and 2 were added for 30 seconds after the polyamide resin was added. Each anionic polymer was prepared using the same general procedure as in Example 1, and the monomer and catalyst ratios were adjusted as appropriate to produce an anionic polymer having the desired molecular weight and molecular weight charge index value.

Table 1 below indicates the dosages of the cationic strength agent (PAE), the anionic polymer and the molecular weight (MW) of the anionic polymers for Examples 4-16. The dosages are given in (lbs/ton) and (weight %).

5

Table 1

Example	Dose of PAE lbs/ton (wt %)	Dose of Anionic Polymer lbs/ton (wt %)	Anionic Polymer (MW)
4	10 (.5)	0	N/A*
5	10 (.5)	2 (.1)	5,000
6	10 (.5)	2 (.1)	10,000
7	10(.5)	2 (.1)	250,000
8	10 (.5)	3 (.15)	5,000
9	10 (.5)	3 (.15)	10,000
10	10 (.5)	3 (.15)	250,000
11	10 (.5)	4 (.2)	5,000
12	10 (.5)	4 (.2)	10,000
13	10 (.5)	4 (.2)	250,000
14	10 (.5)	5 (.25)	5,000
15	10 (.5)	5 (.25)	10,000
16	10 (.5)	5 (.25)	250,000

* Not Applicable

Table 2 summarizes the anionic polymer charge, the molecular weight index value, the wet tensile strength, and the wet strength enhancement that was achieved in Examples 4-16:

10

Table 2

Example	Anionic Polymer Charge mole %	MW Charge Index Value	Wet Tensile Strength	Wet Strength Enhancement %
4	N/A	N/A	3.90	N/A
5	8	400	3.84	-2
6	70	7000	3.79	-3
7	8	20,000	4.30	10
8	8	400	3.95	1
9	70	7,000	3.28	-16
10	8	20,000	4.20	8
11	8	400	4.07	4
12	70	7,000	3.56	-9
13	8	20,000	4.44	14
14	8	400	3.90	0

15	70	7,000	3.46	-11
16	8	20,000	4.21	8

The results indicated that, for a given trial at each specified dose, the trials in which a water-soluble anionic polymer having a molecular weight of at least 50,000 daltons and a molecular weight charge index value that was more than 10,000 (functional promoter) exhibited better results than those systems that used a water-soluble anionic polymer having a molecular weight that was less than 50,000 daltons and a molecular weight charge index value that was less than 10,000. In fact, the low molecular weight anionic polymers (5,000 – 10,000 daltons) across a range of charges yielded poor promotion and in some cases even had negative impact on wet strength. In view of what is known in the art, such results would not have been expected.

EXAMPLES 17-23

1667 g of 0.6% consistency 50/50 hardwood/ softwood furnish containing 200 ppm sulfates and 50 ppm calcium was adjusted to a pH of 7.5 using sodium hydroxide. A dilute solution of polyamide resin was mixed into the pulp slurry at a dosage level of 16 lbs/ ton (0.8 wt%) for 30 seconds.

To evaluate the wet tensile strength of the paper product formed, three 2.8 g handsheets, each approximately 64 square inches (416 cm²), were formed from each batch using a Noble & Wood handsheet former. The formed sheets were pressed between felts in the nip of press rolls, and then drum dried on a rotary drier for one minute at 240°F (116°C). The sheets were conditioned at 73°F (23°C) and 50% relative humidity before measuring the wet tensile with a Thwing-Albert tensile tester. The wet tensile strength of the paper was determined.

To evaluate the effect of adding functional promoters having different molecular weights and different molecular weight charge index values, the procedure described above was repeated, except that dilute solutions containing the anionic polymer indicated below were added for 30 seconds after the polyamide resin was added.

The anionic polymer was prepared using the same general procedure as in Example 1, and the monomer and initiator ratios were adjusted as appropriate to produce an anionic polymer having a desired molecular weight and molecular weight charge index value.

- 5 Table 3 below summarizes the dosages of the cationic strength agent (PAE), the anionic polymer and the molecular weight (MW) of the anionic polymers for Examples 17-23. The dosages are given in (lbs/ton) and weight %.

10

Table 3

Example	Dose of PAE lbs/ton (wt %)	Dose of anionic polymer lbs/ton (wt %)	Anionic Polymer (MW)
17	16 (.8)	0	N/A
18	16 (.8)	4 (.2)	50,000
19	16 (.8)	4 (.2)	50,000
20	16 (.8)	4 (.2)	100,000
21	16 (.8)	4 (.2)	100,000
22	16 (.8)	4 (.2)	200,000
23	16 (.8)	4 (.2)	200,000

Table 4 summarizes the anionic polymer charge, the molecular weight index value, the wet tensile strength, and the wet strength enhancement that was achieved in Examples 17-23:

15

Table 4

Example	Anionic Polymer (Charge) mole %	MW Charge Index Value	Wet Tensile	Wet Strength Enhancement %
17	N/A	N/A	3.69	0
18	20	10,000	4.11	11
19	50	25,000	4.43	20
20	20	20,000	4.27	16
21	50	50,000	4.55	23
22	20	40,000	4.51	22
23	50	100,000	4.49	22

These examples show that the system in which the polymer having an average molecular weight of at least about 50,000 daltons and a molecular weight charge index value of more than 10,000 (functional promoter) imparted significantly more wet strength than the system in which no functional promoter was used. Remarkably, when the molecular weight of the anionic polymer was approximately 50,000, the wet strength enhancement nearly doubled when the charge of the anionic polymer was increased from 20 to 50 mole %.

EXAMPLES 24-27

10 Promotion of Polyamide with Glyoxalated Poly (acrylamide-co-acrylic acid)

This example shows glyoxalated poly(acrylamide-co-acrylic acid) functional promoters of a specified charge enhancing the wet-strength properties of a polyamide resin. The polymers were prepared using the same general procedure as in Example 2, adjusting the monomer and initiator ratios as appropriate to obtain the charge % indicated below in Tables 5 and 6. Backbone molecular weight prior to glyoxylation was approximately 30,000 daltons in these examples. Post-glyoxylation molecular weights were much higher, approximately 1,500,000 daltons. Promotion studies were completed in handsheets using 50/50 hardwood/softwood furnish at a pH of 7.5 and a basis weight of 50 lb/ton.

20 Polyamide wet strength agent was promoted using a glyoxalated poly (acrylamide-co-acrylic acid) copolymer of a specified charge.

Table 5 below indicates the dosages of the cationic strength agent (PAE), the anionic polymer and the molecular weight (MW) of the anionic polymers for Examples 24-27. The dosages are given in lbs/ton and weight % (wt%).

Table 5

Example	Dosage of PAE lbs/ton (wt %)	Dosage of Anionic Polymer lbs/ton (wt %)	Anionic Polymer (MW)
24	20 (1)	0	N/A
25	16 (.8)	4 (.2)	1,500,000

26	16 (.8)	4 (.2)	1,500,000
27	16 (.8)	4 (.2)	1,500,000

Table 6 summarizes the anionic polymer charge, the molecular weight index value, and the wet strength enhancement that was achieved in Examples 24-27:

5

Table 6

Example	Anionic Polymer Charge Mole %	MW Charge Index Value	Wet tensile strength	Wet Strength Enhancement (%)
24	N/A	N/A	3.53	0
25	10	150,000	3.76	7
26	20	300,000	4.07	15
27	30	450,000	4.07	15

The data above shows glyoxalated anionic polyacrylamide functional promoters effectively promoting the strength-enhancing properties of polyamide wet strength agents. When the charge of the anionic polymer increased from 10 to 20 or 30%, respectively, the wet strength enhancement to the paper more than doubled.

EXAMPLES 28-34

These examples show the promotion of a polyamide (PAE) strength resin with a composition of the invention.

The functional promoter from Example 1 was blended with cationic surfactants, as described below. The wet tensile to dry tensile ratio was increased significantly, as shown in Table 7. An additional unforeseen benefit observed with this composition was the ability to add the promoter prior to the PAE where as a single component the user is limited to adding the promoter only after the PAE. This allows the user greater flexibility in his mill process such that the product is much more user friendly and the user is much less likely to harm strength due to poor addition points and/or poor mixing.

5

Table 7

Example	Resin 1	Dose	Resin 2	Dose	Dry Tensile	Wet Tensile	%
28	Blank				12.2	0.32	1
29	PAE resin	16			14.7	3.2	2
30	PAE resin	16	FP	3.1	18.59	4	2
31	PAE resin	16	FP +Surf 1	3.1	16.4	3.9	2
32	Functional promoter (FP)	3.1	PAE	16	14.11	2.7	1
33	FP +Surf 1	3.1	PAE	16	16	3.8	2
34	PAE resin	16	A Polymer +Surf-2	3.1	16.9	4	2

Functional Promoter is from Example 1.

- 10 Surf1 is an imidazole-type surfactant
 Surf2 is a sulfosuccinate-type surfactant

The results show that the PAE resin alone increased dry tensile slightly but increased wet tensile dramatically yielding a greatly improved W/D compared with the blank. Addition of the functional promoter boosts both wet and dry tensile leaving the W/D virtually unchanged. Addition of the composition containing the surfactant "Surf1" enhances W/D by approximately 10% compared with either the PAE alone or the PAE/anionic polymer system. When the functional promoter is added prior to the PAE, the wet tensile is actually decreased by nearly 16% compared with PAE alone rather than improved. However, with the composition is used, the wet tensile is improved by nearly 19% compared to PAE alone, a similar amount to the reverse addition and 41% better than the anionic polymer / PAE system alone. Finally, the composition containing the surfactant "Surf2" also improves W/D vs. PAE.

Example 35

The procedure of Example 31 was repeated, except that instead of using a cationic surfactant, each the following anionic surfactants was
5 tested: odium dioctyl sulfosuccinate, sodium dihexyl sulfosuccinate, sodium diamyl sulfosuccinate, sodium dibutyl sulfosuccinate, sodium bistridecyl sulfosuccinate, sodium salt of sulfated nonylphenoxy poly-(ethyleneoxy) ethanol, and sodium salt of sulfonated chloroparaffin. It was
10 observed that gellation and/or separation occurred when each anionic surfactant was used, such that when the functional promoter and the anionic surfactant treated a fibrous substrate, in conjunction with the cationic strength agent (the PAE resin), the treated fibrous substrate did
not exhibit (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile
15 strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate was treated with the functional promoter and without a surfactant.

Although the present invention has been described in detail with reference to certain preferred versions thereof, other variations are
20 possible. Therefore, the spirit and scope of the appended claims should not be limited to the description of the versions contained therein.

WHAT IS CLAIMED IS:

1. A composition comprising:
 - (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a
5 molecular weight charge index value of at least about 10,000;
 - (b) a cationic surfactant component;wherein when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging
10 from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.
2. The composition of Claim 1, wherein the cationic surfactant
15 component is present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component
3. The composition of Claim 1, wherein the cationic surfactant component is selected from the group consisting of alkylated quaternary
20 amines, alkyl aryl quaternary amines, alkoxyated quaternary amines, imidazolinium quaternary amines, functionalized polysiloxanes, and combinations thereof.
4. The composition of Claim 1, wherein the cationic surfactant component is present in an amount ranging from about 10 % to about
25 50%, based on the total weight of the composition
5. The composition of Claim 4, wherein the cationic surfactant component is present in an amount ranging from about 20% to about 40%, based on the total weight of the composition
6. The composition of Claim 1, wherein when the composition
30 treats a fibrous substrate, in conjunction with a cationic strength agent, the increase in wet tensile strength:dry tensile strength ratio ranges from about at least about 10% to about 50%.

7. The composition of Claim 1, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 5,000,000 daltons.
8. The composition of Claim 1, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 2,000,000 daltons.
9. The composition of Claim 1, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 1,000,000 daltons.
10. The composition of Claim 1, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 750,000 daltons.
11. The composition of Claim 1, wherein the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 1,000,000.
12. The composition of Claim 1, wherein the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 500,000 daltons.
13. The composition of Claim 1, wherein the functional promoter is in solution.
14. The composition of Claim 13, wherein the molecular weight of the functional promoter is less than 5,000,000 daltons.
15. The composition of Claim 1, wherein the functional promoter is selected from the group consisting of copolymers of acrylamide-acrylic acids, copolymers of methacrylic acid, copolymers having alkyl acrylates and acrylic acid, copolymers of alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate copolymers, hydroxy alkyl methacrylate copolymers, copolymers of alkyl vinyl ethers and acrylic acid, anionic polymers made by hydrolyzing an acrylamide polymer, anionic polymers made by polymerizing (i) (methyl)acrylic acid, (ii) (methyl)acrylic acid salts, (iii) 2-acrylamido-2-methylpropane sulfonate, (iv) sulfoethyl-(meth)acrylate, (v) vinylsulfonic acid, (vi) styrene sulfonic acid, (vii) dibasic acids, (viii) salts

of the foregoing monomers, and mixtures thereof, and anionic polymers made with crosslinking agents.

5 16. A composition comprising
 (a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight ranging from about 50,000 daltons to about 500,000 daltons and a molecular weight charge index value of more than 10,000 and less than 500,000,

10 (b) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component,

 wherein when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate
15 exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

20 17. The composition of Claim 16, wherein the molecular weight ranges from about 50,000 to about 250,000 daltons.

 18. The composition of Claim 16, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 100,000 daltons.

25 19. The composition of Claim 16, wherein the functional promoter has a molecular weight ranging from about 300,000 to about 500,000.

 20. The composition of Claim 16, wherein the functional promoter has a molecular weight charge index value ranging from about
30 10,000 to about 100,000.

 21. The composition of Claim 16, wherein the functional promoter has a molecular weight charge index value ranging from about 25,000 to about 100,000.

22. The composition of Claim 16, wherein the functional promoter is in solution.

23. The composition of Claim 16, wherein the functional promoter is selected from the group consisting of copolymers of acrylamide-acrylic acids, copolymers of methacrylic acid, copolymers having alkyl acrylates and acrylic acid, copolymers of alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate copolymers, hydroxy alkyl methacrylate copolymers, copolymers of alkyl vinyl ethers and acrylic acid, anionic polymers made by hydrolyzing an acrylamide polymer, anionic polymers made by polymerizing (i) (methyl)acrylic acid, (ii) (methyl)acrylic acid salts, (iii) 2-acrylamido-2-methylpropane sulfonate, (iv) sulfoethyl-(meth)acrylate, (v) vinylsulfonic acid, (vi) styrene sulfonic acid, (vii) dibasic acids, (vii) salts of the foregoing monomers, and mixtures thereof, and anionic polymers made with crosslinking agents.

24. A composition comprising a wet-strength enhancing amount of

(a) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000,

(b) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component; and

(c) a cationic strength component,

wherein when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

25. The composition of Claim 24, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 500,000 daltons.

26. The composition of Claim 24, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 250,000 daltons.

5 27. The composition of Claim 24, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 100,000 daltons.

28. The composition of Claim 24, wherein the functional promoter has a molecular weight ranging from about 300,000 to about 500,000.

10 29. The composition of Claim 24, wherein the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 100,000.

30. The composition of Claim 24, wherein the functional promoter has a molecular weight charge index value ranging from about 25,000 to about 100,000.

15 31. The composition Claim 24, wherein the functional promoter is in solution.

32. The composition of Claim 31, wherein the molecular weight of the functional promoter is less than 5,000,000 daltons.

20 33. The composition of Claim 24, wherein the functional promoter is selected from the group consisting of copolymers of acrylamide-acrylic acids, copolymers of methacrylic acid, copolymers having alkyl acrylates and acrylic acid, copolymers of alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate copolymers, hydroxy alkyl
25 methacrylate copolymers, copolymers of alkyl vinyl ethers and acrylic acid, anionic polymers made by hydrolyzing an acrylamide polymer, anionic polymers made by polymerizing (i) (methyl)acrylic acid, (ii) (methyl)acrylic acid salts, (iii) 2-acrylamido-2-methylpropane sulfonate, (iv) sulfoethyl-(meth)acrylate, (iv) vinylsulfonic acid, (v) styrene sulfonic acid, (vi) dibasic
30 acids, (vii) salts of the foregoing monomers, and mixtures thereof, and anionic polymers made with crosslinking agents.

34. The composition of Claim 24, wherein the cationic strength component is (i) a polyamide strength resin or (ii) a glyoxylated cationic polymer or (iii) a polyamide strength resin and a cationic starch.

35. The composition of Claim 24, wherein the composition
5 further comprises a fibrous substrate component.

36. The composition of Claim 35, wherein the fibrous substrate component is selected from the group consisting of fine paper pulp slurries, newsprint pulp slurries, board pulp slurries, towel pulp slurries, and tissue pulp slurries.

10 37. The composition of Claim 24, wherein the functional promoter and the cationic strength component are present at a functional promoter-to-cationic strength component ratio ranging from about 1/20 to about 1/1.

38. A paper product comprising the reaction product of:
15 (a) a cationic strength component,
(b) a fibrous substrate component, and
(c) a composition comprising (1) a functional promoter comprising a water-soluble anionic polymer having a molecular weight of at least about 50,000 daltons and a molecular weight charge index value
20 of at least about 10,000 and (2) a cationic surfactant component;

wherein when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile
25 strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

39. The paper product of Claim 38, wherein the functional promoter has a molecular weight ranging from about 50,000 to about
30 500,000 daltons.

40. The paper product of Claim 38, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 250,000 daltons.

41. The paper product of Claim 38, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 100,000 daltons.

5 42. The paper product of Claim 38, wherein the functional promoter has a molecular weight ranging from about 300,000 to about 500,000.

43. The paper product of Claim 38, wherein the functional promoter has a molecular weight charge index value ranging from about 10,000 to about 100,000.

10 44. The paper product of Claim 38, wherein the functional promoter has a molecular weight charge index value ranging from about 25,000 to about 100,000.

45. The paper product of Claim 38, wherein the functional polymer is solution.

15 46. The paper product of Claim 38, wherein the molecular weight of the functional promoter is less than 5,000,000.

47. The paper product of Claim 38, wherein the cationic strength component is (i) a polyamide strength resin or (ii) a glyoxylated cationic polymer or (iii) a polyamide strength resin and a cationic starch.

20 48. The paper product of Claim 38, wherein the functional promoter is selected from the group consisting of copolymers of acrylamide-acrylic acids, copolymers of methacrylic acid, copolymers having alkyl acrylates and acrylic acid, copolymers of alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate copolymers, hydroxy alkyl
25 methacrylate copolymers, copolymers of alkyl vinyl ethers and acrylic acid, anionic polymers made by hydrolyzing an acrylamide polymer, anionic polymers made by polymerizing (i) (methyl)acrylic acid, (ii) (methyl)acrylic acid salts, (iii) 2-acrylamido-2-methylpropane sulfonate, (iv) sulfoethyl-(meth)acrylate, (iv) vinylsulfonic acid, (v) styrene sulfonic acid, (vi) dibasic
30 acids, (vii) salts of the foregoing monomers, and mixtures thereof, and anionic polymers made with crosslinking agents.

49. The paper product of Claim 38, wherein the paper product is a board paper product.

50. The paper product of Claim 38, wherein the functional promoter and the cationic strength component are present at a functional promoter:cationic strength component ratio ranging from about 1/20 to about 1/1.

5 51. A method for making a paper product comprising adding to a pulp slurry containing a fibrous substrate component a composition comprising:

(a) a composition comprising (1) a functional promoter comprising (i) a water-soluble anionic polymer having a molecular weight
10 of at least about 50,000 daltons and a molecular weight charge index value of at least about 10,000,

(2) a cationic surfactant component present in an amount of less than about 50 wt %, based on the combined weight of the water-soluble anionic polymer and the cationic surfactant component, and

15 (3) a cationic strength component,

wherein when the composition treats a fibrous substrate, in conjunction with a cationic strength agent, the treated fibrous substrate exhibits (i) a ratio of wet tensile strength to dry tensile strength ranging from about 1:5 to about 1:2 and (ii) an increase in a ratio of wet tensile
20 strength to dry tensile strength of at least about 10%, as compared to when the fibrous substrate is treated with the functional promoter and without a surfactant.

52. The method of Claim 51, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 500,000
25 daltons.

53. The method of Claim 51, wherein the functional promoter has a molecular weight ranging from about 50,000 to about 250,000 daltons.

54. The method of Claim 51, wherein the functional promoter
30 has a molecular weight ranging from about 50,000 to about 100,000 daltons.

55. The method of Claim 51, wherein the functional promoter has a molecular weight ranging from about 300,000 to about 500,000 and charge.

56. The method of Claim 51, wherein the functional promoter
5 has a molecular weight charge index value ranging from about 10,000 to about 100,000.

57. The method of Claim 51, wherein the functional promoter has a molecular weight charge index value ranging from about 25,000 to about 100,000.

10 58. The method of Claim 51, wherein the functional promoter is in solution.

59. The method of Claim 51, wherein the molecular weight of the functional promoter is less than 5,000,000 daltons.

60. The method of Claim 51, wherein the functional promoter is
15 is selected from the group consisting of copolymers of acrylic acid, copolymers of acrylamide-acrylic acids, copolymers of methacrylic acid, copolymers having alkyl acrylates and acrylic acid, copolymers of alkyl methacrylates and acrylic acid, anionic hydroxyalkyl acrylate copolymers, hydroxy alkyl methacrylate copolymers, copolymers of alkyl vinyl ethers
20 and acrylic acid, anionic polymers made by hydrolyzing an acrylamide polymer, anionic polymers made by polymerizing (i) (methyl)acrylic acid, (ii) (methyl)acrylic acid salts, (iii) 2-acrylamido-2-methylpropane sulfonate, (iv) sulfoethyl-(meth)acrylate, (iv) vinylsulfonic acid, (v) styrene sulfonic acid, (vi) dibasic acids, (vii) salts of the foregoing monomers, and mixtures
25 thereof, and anionic polymers made with crosslinking agents.

61. The method of Claim 51, wherein the cationic strength component is a polyamide wet strength resin or a glyoxylated cationic polymer or a polyamide wet strength resin and a cationic starch.

62. The method of Claim 51, wherein the fibrous substrate
30 component is selected from the group consisting of fine paper pulp slurries, newsprint pulp slurries, board pulp slurries, towel pulp slurries, and tissue pulp slurries.

63. The method of Claim 51, wherein the fibrous substrate is a board pulp slurry.

64. The method of Claim 51, wherein the functional promoter and the cationic strength component are present at a functional
5 promoter:cationic strength component ratio ranging from about 1/20 to about 1/1.

65. The method of Claim 51, wherein the composition is added to the slurry at a dosage of at least about 0.1 lb/ton and the cationic
10 strength component is added to the slurry at a dosage of at least about 0.1 lb/ton.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/003412

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21H17/72 D21H23/76
 //D21H17:29,17:42,17:55,21:20,21:24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAPERCHEM

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	WO 2004/001129 A (BAYER CHEMICALS CORP) 31 December 2003 (2003-12-31) cited in the application the whole document	1,6-65
A	US 6 264 791 B1 (LINDSAY JEFFREY D ET AL) 24 July 2001 (2001-07-24) column 3, line 30 - column 7, line 46	1-3,13, 15,16, 22,23, 38,45,48
A	US 3 844 880 A (MEISEL F ET AL) 29 October 1974 (1974-10-29) column 3, line 44 - line 51; claims 1,3-5,9-11; example IV ----- -/--	38,48, 51,60, 62,65

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

22 July 2004

Date of mailing of the international search report

28/07/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Nestby, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2004/003412

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 750 489 A (GARCIA RIGOBERTO FELIPE ET AL) 12 May 1998 (1998-05-12) column 3, line 4 - column 10, line 49 -----	1,2,7-23
A	US 4 517 285 A (WOODWARD ANTONY I ET AL) 14 May 1985 (1985-05-14) -----	
A	US 3 816 556 A (COSCIA A ET AL) 11 June 1974 (1974-06-11) -----	
A	EP 0 549 925 A (HERCULES INC) 7 July 1993 (1993-07-07) -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2004/003412

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 2004001129	A	31-12-2003	US 2003234089 A1 WO 2004001129 A1	25-12-2003 31-12-2003
US 6264791	B1	24-07-2001	AU 1086301 A WO 0131124 A1	08-05-2001 03-05-2001
US 3844880	A	29-10-1974	BE 778320 A1 CA 944906 A1 DE 2202985 A1 FR 2123010 A5 IT 948276 B NL 7200829 A	20-07-1972 09-04-1974 17-08-1972 01-09-1972 30-05-1973 25-07-1972
US 5750489	A	12-05-1998	AU 701587 B2 AU 2525695 A BR 9507646 A CA 2187520 A1 WO 9531528 A1 EP 0759062 A1 JP 9507695 T ZA 9503887 A	04-02-1999 05-12-1995 09-09-1997 23-11-1995 23-11-1995 26-02-1997 05-08-1997 12-11-1996
US 4517285	A	14-05-1985	EP 0106706 A1 ES 8606559 A1 JP 60081396 A	25-04-1984 01-10-1986 09-05-1985
US 3816556	A	11-06-1974	AR 194455 A1 AT 328290 B AT 509173 A AU 5472173 A BE 800692 A1 DE 2326292 A1 FR 2187874 A1 GB 1416957 A IT 985202 B JP 49061412 A NL 7306894 A	13-07-1973 10-03-1976 15-05-1975 24-10-1974 10-12-1973 20-12-1973 18-01-1974 10-12-1975 30-11-1974 14-06-1974 11-12-1973
EP 0549925	A	07-07-1993	US 5316623 A AU 659895 B2 AU 2996092 A CA 2084851 A1 DE 69204270 D1 DE 69204270 T2 EP 0549925 A1 ES 2076000 T3 MX 9207099 A1	31-05-1994 01-06-1995 10-06-1993 10-06-1993 28-09-1995 25-01-1996 07-07-1993 16-10-1995 01-06-1993